

BRENNTAG s.p.a.

Sede Legale e amministrativa
Milanofiori Strada 6, Pal. A/13
20057 Assago(MI)
Tel. 02 48333.0. (ric. aut.)
Telefax 02 48333.330

Cap. Soc. € 18.300.000,00 i.v.
R.E.A. MI 472696
Registro Imprese di Milano
e C.F. n. 00835510157
Part. IVA IT 00835510157

Società con socio unico

Società soggetta all'attività di direzione e coordinamento da parte della Brenntag SE



TECHNICAL DATA SHEET

PRODUCT NAME: CARBOPUR 54

PRODUCT CODE: T196940

RELATED ARTICLES: E54BB600

DESCRIPTION

Black granules.

ANALYTICAL DATA

C / I	ANALYSIS DESCRIPTION	NOTE	MAX MIN TIP	VALUE	TOLERANCE	U.M.	ANALYTICAL METHOD
I	IODINE INDEX		TYPICAL	750		mg/g	ASTM 4607
I	SPECIFIC SURFACE AREA BET (m2/g)		TYPICAL	800			ASTM 3663
I	APPARENT DENSITY		TYPICAL	600		kg/m3	ASTM 2854
I	HARDNESS		TYPICAL	95		%	ASTM 3802
I	ASHES		TYPICAL	10		%	ASTM 2866
I	pH	Alkaline	TYPICAL				ASTM 3838
I	ADSORPTION CC14		TYPICAL	50		%	ASTM 3467

C/I = CONTROLLED / INFORMATIVE

FURTHER INFORMATION

Data provided by Brenntag's supplier
SM: Supplier's internal analytical method.

THIS DOCUMENT IS ELECTRONICALLY ISSUED AND NOT SIGNED IN

REVISION N° 00001 OF 26/05/2022

All our certifications can be downloaded on website www.brenntag.com/en-it/sustainability/certifications/